



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Barcaldine Regional

Above-ground:

A

In-ground:

B

Building member details

Barge boards

Environment:

Exposed

Target design life (years):

15

Properties for [damar minyak]

[Download report](#)

Standard trade name	damar minyak
Botanical name	<i>Agathis spp.</i>
Synonyms	NA
Origin	Asia-Pacific
Schedule	Schedule C
Hardwood	No
Density (kg/m3)	480
Durability above-ground	(4)
Durability in-ground	(4)
Hardness	VS
Joint dry (JD)	JD4
Joint green (JG)	J4
Strength dry (SD)	(SD7)
Strength green (SG)	(S6)
Bushfire resisting	No

Standard trade name	damar minyak
Lyctine susceptibility	NS
Termite resistance	NR
Advisory codes	A4

Target design life, hazard zones and conditions for use

Botanical name	<i>Agathis spp.</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	H3!
15 years Above-ground:D	H3!
15 years In-ground:A	H4!
15 years In-ground:B	H4!
15 years In-ground:C	H4!
15 years In-ground:D	H4!

Botanical name	<i>Agathis spp.</i>
50 years protected	Approved
50 years Above-ground:A	H3!, C16
50 years Above-ground:B	H3!, C16
50 years Above-ground:C	H3!, C16
50 years Above-ground:D	H3!, C16
50 years In-ground:A	H5!
50 years In-ground:B	H5!
50 years In-ground:C	H5!
50 years In-ground:D	H5!

QTimber (<http://qtimber.daf.qld.gov.au>)
