



Published on QTimber (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Barcoo Shire

Above-ground:

A

In-ground:

A

Building member details

Rafters and ridges

Environment:

Exposed

Target design life (years):

50

Properties for [amoora]

[Download report](#)

Standard trade name	amoora
Botanical name	<i>Amoora spp.</i>
Synonyms	NA
Origin	Asia-Pacific
Schedule	Schedule C
Hardwood	Yes
Density (kg/m3)	555
Durability above-ground	(3)
Durability in-ground	3
Hardness	S
Joint dry (JD)	JD4
Joint green (JG)	J4
Strength dry (SD)	(SD6)
Strength green (SG)	(S5)
Bushfire resisting	No

Standard trade name	amoora
Lyctine susceptibility	(SL)
Termite resistance	NR
Advisory codes	

Target design life, hazard zones and conditions for use

Botanical name	<i>Amoora spp.</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	C5
15 years In-ground:B	C5
15 years In-ground:C	C5
15 years In-ground:D	C5

Botanical name	<i>Amoora spp.</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Not approved
50 years Above-ground:C	Not approved
50 years Above-ground:D	Not approved
50 years In-ground:A	H5!
50 years In-ground:B	C8
50 years In-ground:C	Not approved
50 years In-ground:D	Not approved

QTimber (<http://qtimber.daf.qld.gov.au>)