



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Brisbane City

Above-ground:

D

In-ground:

C

Building member details

Boards (non-structural)

Environment:

Exposed

Target design life (years):

15

Properties for [blackbutt]

[Download report](#)

Standard trade name	blackbutt
Botanical name	<i>Eucalyptus pilularis</i>
Synonyms	NA
Origin	Queensland-south, Australia
Schedule	Schedule B
Hardwood	Yes
Density (kg/m³)	930
Durability above-ground	(1)
Durability in-ground	(2)
Hardness	H
Joint dry (JD)	JD2
Joint green (JG)	J2
Strength dry (SD)	(SD2)
Strength green (SG)	(S1)
Bushfire resisting	Yes

Standard trade name	blackbutt
Lyctine susceptibility	NS
Termite resistance	R
Advisory codes	

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus pilularis</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	Approved
15 years In-ground:B	C2
15 years In-ground:C	C3
15 years In-ground:D	C4

Botanical name	<i>Eucalyptus pilularis</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Approved
50 years Above-ground:C	Approved
50 years Above-ground:D	Approved
50 years In-ground:A	C3, C11
50 years In-ground:B	C7, C11
50 years In-ground:C	C8, C11
50 years In-ground:D	C8, C11

QTimber (<http://qtimber.daf.qld.gov.au>)