



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Brisbane City

Above-ground:

D

In-ground:

C

Building member details

Boards (non-structural)

Environment:

Exposed

Target design life (years):

15

Properties for [cypress, white]

[Download report](#)

Standard trade name	cypress, white
Botanical name	<i>Callitris glaucophylla</i>
Synonyms	NA
Origin	Queensland-central, Queensland-south, Australia
Schedule	Schedule B
Hardwood	No
Density (kg/m³)	675
Durability above-ground	(1)
Durability in-ground	(2)
Hardness	F
Joint dry (JD)	JD3
Joint green (JG)	J3
Strength dry (SD)	(SD6)
Strength green (SG)	(S4)

Standard trade name	cypress, white
Bushfire resisting	No
Lyctine susceptibility	NS
Termite resistance	R
Advisory codes	A5

Target design life, hazard zones and conditions for use

Botanical name	<i>Callitris glaucophylla</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	Approved
15 years In-ground:B	C2
15 years In-ground:C	C3
15 years In-ground:D	C4

Botanical name	<i>Callitris glaucophylla</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Approved
50 years Above-ground:C	Approved
50 years Above-ground:D	Approved
50 years In-ground:A	C1
50 years In-ground:B	C13
50 years In-ground:C	C14
50 years In-ground:D	C15

QTimber (<http://qtimber.daf.qld.gov.au>)
