



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Brisbane City

Above-ground:

D

In-ground:

C

Building member details

Boards (non-structural)

Environment:

Exposed

Target design life (years):

15

Properties for [durian]

[Download report](#)

Standard trade name	durian
Botanical name	<i>Durio spp. and Neesia spp.</i>
Synonyms	NA
Origin	Asia-Pacific
Schedule	Schedule C
Hardwood	Yes
Density (kg/m3)	575-640
Durability above-ground	(4)
Durability in-ground	(4)
Hardness	F
Joint dry (JD)	JD4
Joint green (JG)	
Strength dry (SD)	(SD4)
Strength green (SG)	(S3)
Bushfire resisting	No
Lyctine susceptibility	(SL)

Standard trade name	durian
Termite resistance	NR
Advisory codes	

Target design life, hazard zones and conditions for use

Botanical name	<i>Durio spp. and Neesia spp.</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	H3!
15 years In-ground:A	C5
15 years In-ground:B	C5
15 years In-ground:C	C5
15 years In-ground:D	C6

Botanical name	<i>Durio spp. and Neesia spp.</i>
50 years protected	Approved
50 years Above-ground:A	H3!
50 years Above-ground:B	H3!
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	H5!
50 years In-ground:B	C8
50 years In-ground:C	Not approved
50 years In-ground:D	Not approved

QTimber (<http://qtimber.daf.qld.gov.au>)