



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Brisbane City

Above-ground:

D

In-ground:

C

Building member details

Joinery (non-structural)

Environment:

Exposed

Target design life (years):

15

Properties for [softwoods, imported]

[Download report](#)

Standard trade name	softwoods, imported
Botanical name	<i>numerous species</i>
Synonyms	NA
Origin	
Schedule	Schedule A
Hardwood	No
Density (kg/m ³)	380-560
Durability above-ground	(4)
Durability in-ground	(4)
Hardness	VS, S
Joint dry (JD)	JD5
Joint green (JG)	J6
Strength dry (SD)	(SD8)
Strength green (SG)	(S7)
Bushfire resisting	No
Lyctine susceptibility	NS

Standard trade name	softwoods, imported
Termite resistance	NR
Advisory codes	A4, A5

Target design life, hazard zones and conditions for use

Botanical name	<i>numerous species</i>
5 years above-ground	Approved
15 years protected	C16
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	H3!
15 years In-ground:A	H4!
15 years In-ground:B	H4!
15 years In-ground:C	H4!
15 years In-ground:D	H4!

Botanical name	<i>numerous species</i>
50 years protected	C16
50 years Above-ground:A	H3!
50 years Above-ground:B	H3!
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	H5!
50 years In-ground:B	H5!
50 years In-ground:C	H5!
50 years In-ground:D	H5!

QTimber (<http://qtimber.daf.qld.gov.au>)
