



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Carpentaria Shire

Above-ground:

A

In-ground:

C

Building member details

Brackets

Environment:

Protected

Target design life (years):

15

Properties for [ash, alpine]

[Download report](#)

Standard trade name	ash, alpine	ash, alpine
Botanical name	<i>Eucalyptus delegatensis</i>	<i>Eucalyptus delegatensis</i>
Synonyms	NA	NA
Origin	New South Wales, Victoria	Tasmania
Schedule	Schedule B	Schedule B
Hardwood	Yes	Yes
Density (kg/m3)	675	675
Durability above-ground	(3)	(3)
Durability in-ground	(4)	4
Hardness	F	F
Joint dry (JD)	JD3	JD3
Joint green (JG)	J3	J3
Strength dry (SD)	(SD4)	(SD4)
Strength green (SG)	(S4)	(S4)
Bushfire resisting	No	No

Standard trade name	ash, alpine	ash, alpine
Lyctine susceptibility	NS	(SL)
Termite resistance	NR	NR
Advisory codes		

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus delegatensis</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	C17
15 years Above-ground:B	C17
15 years Above-ground:C	C17
15 years Above-ground:D	C17
15 years In-ground:A	C5
15 years In-ground:B	C5
15 years In-ground:C	C5
15 years In-ground:D	C6

Botanical name	<i>Eucalyptus delegatensis</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	H3!
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	H5!
50 years In-ground:B	C8
50 years In-ground:C	Not approved
50 years In-ground:D	Not approved

QTimber (<http://qtimber.daf.qld.gov.au>)