



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Palm Island Aboriginal Shire

Above-ground:

D

In-ground:

D

Building member details

Bearers (*e.g. un-roofed deck*)

Environment:

Exposed

Target design life (years):

50

Properties for [ash, silvertop]

[Download report](#)

Standard trade name	ash, silvertop
Botanical name	<i>Eucalyptus sieberi</i>
Synonyms	NA
Origin	Australia
Schedule	Schedule B
Hardwood	Yes
Density (kg/m³)	820
Durability above-ground	(2)
Durability in-ground	3
Hardness	H
Joint dry (JD)	JD2
Joint green (JG)	J2
Strength dry (SD)	(SD3)
Strength green (SG)	(S2)
Bushfire resisting	Yes

Standard trade name	ash, silvertop
Lyctine susceptibility	NS
Termite resistance	NR
Advisory codes	

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus sieberi</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	C5
15 years In-ground:B	C5
15 years In-ground:C	C5
15 years In-ground:D	C5

Botanical name	<i>Eucalyptus sieberi</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Approved
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	H5!
50 years In-ground:B	C7
50 years In-ground:C	C9
50 years In-ground:D	C9

QTimber (<http://qtimber.daf.qld.gov.au>)