



Published on QTimber (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Palm Island Aboriginal Shire

Above-ground:

D

In-ground:

D

Building member details

Poles, posts (*House/deck, in-ground*)

Environment:

[In-ground](#)

Target design life (years):

50

Properties for [gum, rose]

[Download report](#)

Standard trade name	gum, rose
Botanical name	<i>Eucalyptus grandis</i>
Synonyms	NA
Origin	Queensland-north, Queensland-central, Queensland-south, Australia
Schedule	Schedule B
Hardwood	Yes
Density (kg/m³)	800
Durability above-ground	(2)
Durability in-ground	3
Hardness	F
Joint dry (JD)	JD2
Joint green (JG)	J3
Strength dry (SD)	(SD4)

Standard trade name	gum, rose
Strength green (SG)	(S2)
Bushfire resisting	No
Lyctine susceptibility	NS
Termite resistance	NR
Advisory codes	A2

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus grandis</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	C5
15 years In-ground:B	C5
15 years In-ground:C	C5
15 years In-ground:D	C5

Botanical name	<i>Eucalyptus grandis</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Approved
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	H5!
50 years In-ground:B	C7
50 years In-ground:C	C9
50 years In-ground:D	C9

QTimber (<http://qtimber.daf.qld.gov.au>)