



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Palm Island Aboriginal Shire

Above-ground:

D

In-ground:

D

Building member details

Brackets

Environment:

Protected

Target design life (years):

15

Properties for [box, brush]

[Download report](#)

Standard trade name	box, brush
Botanical name	<i>Lophostemon confertus</i>
Synonyms	<i>Tristania conferta</i>
Origin	Queensland-north, Queensland-south, Australia
Schedule	Schedule B
Hardwood	Yes
Density (kg/m³)	880
Durability above-ground	(3)
Durability in-ground	3
Hardness	H
Joint dry (JD)	JD2
Joint green (JG)	J2
Strength dry (SD)	(SD3)
Strength green (SG)	(S2)

Standard trade name	box, brush
Bushfire resisting	No
Lyctine susceptibility	NS
Termite resistance	R
Advisory codes	A1

Target design life, hazard zones and conditions for use

Botanical name	<i>Lophostemon confertus</i>
5 years above-ground	Approved
15 years protected	C16
15 years Above-ground:A	C16
15 years Above-ground:B	C16
15 years Above-ground:C	C16
15 years Above-ground:D	C16
15 years In-ground:A	C5
15 years In-ground:B	C5
15 years In-ground:C	C5
15 years In-ground:D	C5

Botanical name	<i>Lophostemon confertus</i>
50 years protected	C16
50 years Above-ground:A	C16
50 years Above-ground:B	H3!
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	H5!
50 years In-ground:B	C7
50 years In-ground:C	C9
50 years In-ground:D	C9

QTimber (<http://qtimber.daf.qld.gov.au>)
