



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

Location details

Paroo Shire

Above-ground:

A

In-ground:

B

Building member details

Bracing

Environment:

Exposed

Target design life (years):

50

Properties for [box, northern]

[Download report](#)

Standard trade name	box, northern
Botanical name	<i>Tristania spp.</i>
Synonyms	NA
Origin	Asia-Pacific
Schedule	Schedule C
Hardwood	Yes
Density (kg/m3)	940-1280
Durability above-ground	(2)
Durability in-ground	(2)
Hardness	H, VH
Joint dry (JD)	JD1
Joint green (JG)	J1
Strength dry (SD)	(SD2)
Strength green (SG)	(S1)
Bushfire resisting	No

Standard trade name	box, northern
Lyctine susceptibility	(SL)
Termite resistance	NR
Advisory codes	

Target design life, hazard zones and conditions for use

Botanical name	<i>Tristania spp.</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	Approved
15 years In-ground:B	C2
15 years In-ground:C	C3
15 years In-ground:D	C4

Botanical name	<i>Tristania spp.</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Approved
50 years Above-ground:C	H3!
50 years Above-ground:D	H3!
50 years In-ground:A	C3
50 years In-ground:B	C7
50 years In-ground:C	C8
50 years In-ground:D	C8

QTimber (<http://qtimber.daf.qld.gov.au>)