



Published on *QTimber* (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Build with timbers summary](#) > [Build with timbers summary](#) > [Build with timbers summary](#) >

[Help](#)

## Location details

Rockhampton Regional

### Above-ground:

C

### In-ground:

C

## Building member details

Poles, posts (*Pergolas, in-ground, accessible*)

### Environment:

[In-ground](#)

### Target design life (years):

15

## Properties for [blackbutt]

[Download report](#)

|                                   |                                |
|-----------------------------------|--------------------------------|
| <b>Standard trade name</b>        | <b>blackbutt</b>               |
| <b>Botanical name</b>             | <i>Eucalyptus pilularis</i>    |
| <b>Synonyms</b>                   | NA                             |
| <b>Origin</b>                     | Queensland-south,<br>Australia |
| <b>Schedule</b>                   | Schedule B                     |
| <b>Hardwood</b>                   | Yes                            |
| <b>Density (kg/m<sup>3</sup>)</b> | 930                            |
| <b>Durability above-ground</b>    | (1)                            |
| <b>Durability in-ground</b>       | (2)                            |
| <b>Hardness</b>                   | H                              |
| <b>Joint dry (JD)</b>             | JD2                            |
| <b>Joint green (JG)</b>           | J2                             |
| <b>Strength dry (SD)</b>          | (SD2)                          |
| <b>Strength green (SG)</b>        | (S1)                           |
| <b>Bushfire resisting</b>         | Yes                            |

|                               |                  |
|-------------------------------|------------------|
| <b>Standard trade name</b>    | <b>blackbutt</b> |
| <b>Lyctine susceptibility</b> | NS               |
| <b>Termite resistance</b>     | R                |
| <b>Advisory codes</b>         |                  |

## Target design life, hazard zones and conditions for use

|                                |                                    |
|--------------------------------|------------------------------------|
| <b>Botanical name</b>          | <b><i>Eucalyptus pilularis</i></b> |
| <b>5 years above-ground</b>    | Approved                           |
| <b>15 years protected</b>      | Approved                           |
| <b>15 years Above-ground:A</b> | Approved                           |
| <b>15 years Above-ground:B</b> | Approved                           |
| <b>15 years Above-ground:C</b> | Approved                           |
| <b>15 years Above-ground:D</b> | Approved                           |
| <b>15 years In-ground:A</b>    | Approved                           |
| <b>15 years In-ground:B</b>    | C2                                 |
| <b>15 years In-ground:C</b>    | C3                                 |
| <b>15 years In-ground:D</b>    | C4                                 |

|                                |                                    |
|--------------------------------|------------------------------------|
| <b>Botanical name</b>          | <b><i>Eucalyptus pilularis</i></b> |
| <b>50 years protected</b>      | Approved                           |
| <b>50 years Above-ground:A</b> | Approved                           |
| <b>50 years Above-ground:B</b> | Approved                           |
| <b>50 years Above-ground:C</b> | Approved                           |
| <b>50 years Above-ground:D</b> | Approved                           |
| <b>50 years In-ground:A</b>    | C3, C11                            |
| <b>50 years In-ground:B</b>    | C7, C11                            |
| <b>50 years In-ground:C</b>    | C8, C11                            |
| <b>50 years In-ground:D</b>    | C8, C11                            |

QTimber (<http://qtimber.daf.qld.gov.au>)