

Location details

Tablelands Regional

Above-ground:

B

In-ground:

D

Building member details

Battens (*External wall*)

Environment:

Exposed

Target design life (years):

15

Properties for [blackbutt]

[Download report](#)

| | |
|--------------------------------|--------------------------------|
| Standard trade name | blackbutt |
| Botanical name | <i>Eucalyptus pilularis</i> |
| Synonyms | NA |
| Origin | Queensland-south, Australia |
| Schedule | Schedule B |
| Hardwood | Yes |
| Density (kg/m3) | 930 |
| Durability above-ground | (1) |
| Durability in-ground | (2) |
| Hardness | H |
| Joint dry (JD) | JD2 |
| Joint green (JG) | J2 |
| Strength dry (SD) | (SD2) |

| | |
|-------------------------------|------------------|
| Standard trade name | blackbutt |
| Strength green (SG) | (S1) |
| Bushfire resisting | Yes |
| Lyctine susceptibility | NS |
| Termite resistance | R |
| Advisory codes | |

Target design life, hazard zones and conditions for use

| Botanical name | <i>Eucalyptus pilularis</i> |
|--------------------------------|------------------------------------|
| 5 years above-ground | Approved |
| 15 years protected | Approved |
| 15 years Above-ground:A | Approved |
| 15 years Above-ground:B | Approved |
| 15 years Above-ground:C | Approved |
| 15 years Above-ground:D | Approved |
| 15 years In-ground:A | Approved |
| 15 years In-ground:B | C2 |
| 15 years In-ground:C | C3 |
| 15 years In-ground:D | C4 |

| Botanical name | <i>Eucalyptus pilularis</i> |
|--------------------------------|------------------------------------|
| 50 years protected | Approved |
| 50 years Above-ground:A | Approved |
| 50 years Above-ground:B | Approved |
| 50 years Above-ground:C | Approved |
| 50 years Above-ground:D | Approved |
| 50 years In-ground:A | C3, C11 |
| 50 years In-ground:B | C7, C11 |
| 50 years In-ground:C | C8, C11 |
| 50 years In-ground:D | C8, C11 |

QTimber (<http://qtimber.daf.qld.gov.au>)
