

Properties

[Download pdf](#)

Botanical name	<i>Eucalyptus andrewsii</i> ssp. <i>andrewsii</i>	<i>Eucalyptus andrewsii</i> ssp. <i>campanulata</i>
Synonyms	<i>Eucalyptus campanulata</i>	<i>Eucalyptus campanulata</i>
Origin	Queensland-central, Queensland-south, Australia	Queensland-south, Australia
Schedule	Schedule B	Schedule B
Hardwood	Yes	Yes
Density (kg/m³)	880	960
Durability above-ground	(2)	(2)
Durability in-ground	(2)	(2)
Hardness	H	H
Joint dry (JD)	JD2	JD1
Joint green (JG)	J2	J2
Strength dry (SD)	(SD3)	(SD3)
Strength green (SG)	(S2)	(S2)
Bushfire resisting	No	No
Lyctine susceptibility	(SL)	(SL)
Termite resistance	R	R
Advisory codes	A1	A1

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus andrewsii</i> ssp. <i>andrewsii</i>	<i>Eucalyptus andrewsii</i> ssp. <i>campanulata</i>
5 years above-ground	Approved	Approved
15 years protected	C10, C12	C10, C12
15 years Above-ground:A	C10, C12	C10, C12
15 years Above-ground:B	C10, C12	C10, C12
15 years Above-ground:C	C10, C12	C10, C12

Botanical name	<i>Eucalyptus andrewsii</i> ssp. <i>andrewsii</i>	<i>Eucalyptus andrewsii</i> ssp. <i>campanulata</i>
15 years Above-ground:D	C10, C12	C10, C12
15 years In-ground:A	Approved	Approved
15 years In-ground:B	C2	C2
15 years In-ground:C	C3	C3
15 years In-ground:D	C4	C4

Botanical name	<i>Eucalyptus andrewsii</i> ssp. <i>andrewsii</i>	<i>Eucalyptus andrewsii</i> ssp. <i>campanulata</i>
50 years protected	C10, C12	C10, C12
50 years Above-ground:A	C10, C12	C10, C12
50 years Above-ground:B	C10, C12	C10, C12
50 years Above-ground:C	C10, C12, H3!	C10, C12, H3!
50 years Above-ground:D	C10, C12, H3!	C10, C12, H3!
50 years In-ground:A	C3, C11	C3, C11
50 years In-ground:B	C7, C11	C7, C11
50 years In-ground:C	C8, C11	C8, C11
50 years In-ground:D	C8, C11	C8, C11

QTimber (<http://qtimber.daf.qld.gov.au>)
