



Published on QTimber (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Timber Factsheet](#) >

Properties

[Download pdf](#)

Botanical name	<i>Thuja plicata</i>
Synonyms	NA
Origin	North America
Schedule	Schedule C
Hardwood	No
Density (kg/m3)	380
Durability above-ground	(2)
Durability in-ground	(2)
Hardness	VS
Joint dry (JD)	JD5
Joint green (JG)	
Strength dry (SD)	(SD8)
Strength green (SG)	(S7)
Bushfire resisting	No
Lyctine susceptibility	NS
Termite resistance	R
Advisory codes	A9

Target design life, hazard zones and conditions for use

Botanical name	<i>Thuja plicata</i>
5 years above-ground	Approved
15 years protected	C16
15 years Above-ground:A	C16
15 years Above-ground:B	C16
15 years Above-ground:C	C16
15 years Above-ground:D	C16
15 years In-ground:A	Approved
15 years In-ground:B	C2
15 years In-ground:C	C3

Botanical name	<i>Thuja plicata</i>
15 years In-ground:D	C4

Botanical name	<i>Thuja plicata</i>
50 years protected	C16
50 years Above-ground:A	C16
50 years Above-ground:B	C16
50 years Above-ground:C	C16, H3!
50 years Above-ground:D	C16, H3!
50 years In-ground:A	C3
50 years In-ground:B	C7
50 years In-ground:C	C8
50 years In-ground:D	C8

QTimber (<http://qtimber.daf.qld.gov.au>)
