



Published on QTimber (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Timber Factsheet](#) >

Properties

[Download pdf](#)

Botanical name	<i>Eucalyptus drepanophylla</i>	<i>Eucalyptus paniculata</i>
Synonyms	<i>Eucalyptus decepta</i> , <i>Eucalyptus siderophloia</i>	<i>Eucalyptus decepta</i> , <i>Eucalyptus siderophloia</i>
Origin	Queensland-north, Queensland-central, Queensland-south	Australia
Schedule	Schedule B	Schedule B
Hardwood	Yes	Yes
Density (kg/m3)	1105	1105
Durability above-ground	(1)	(1)
Durability in-ground	1	1
Hardness	VH	VH
Joint dry (JD)	JD1	JD1
Joint green (JG)	J1	J1
Strength dry (SD)	(SD1)	(SD1)
Strength green (SG)	(S7)	(S7)
Bushfire resisting	No	No
Lyctine susceptibility	NS	NS
Termite resistance	R	R
Advisory codes		

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus drepanophylla</i>	<i>Eucalyptus paniculata</i>
5 years above-ground	Approved	Approved
15 years protected	Approved	Approved
15 years Above-ground:A	Approved	Approved
15 years Above-ground:B	Approved	Approved
15 years Above-ground:C	Approved	Approved
15 years Above-ground:D	Approved	Approved
15 years In-ground:A	Approved	Approved

Botanical name	<i>Eucalyptus drepanophylla</i>	<i>Eucalyptus paniculata</i>
15 years In-ground:B	Approved	Approved
15 years In-ground:C	Approved	Approved
15 years In-ground:D	C1	C1

Botanical name	<i>Eucalyptus drepanophylla</i>	<i>Eucalyptus paniculata</i>
50 years protected	Approved	Approved
50 years Above-ground:A	Approved	Approved
50 years Above-ground:B	Approved	Approved
50 years Above-ground:C	Approved	Approved
50 years Above-ground:D	Approved	Approved
50 years In-ground:A	C1	C1
50 years In-ground:B	C7, C14	C7, C14
50 years In-ground:C	C8	C8
50 years In-ground:D	C8	C8

QTimber (<http://qtimber.daf.qld.gov.au>)
