



Published on QTimber (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Timber Factsheet](#) >

Properties

[Download pdf](#)

Botanical name	<i>Eucalyptus sideroxylon</i>
Synonyms	NA
Origin	Queensland-south, Australia
Schedule	Schedule B
Hardwood	Yes
Density (kg/m3)	1090
Durability above-ground	(1)
Durability in-ground	1
Hardness	VH
Joint dry (JD)	JD1
Joint green (JG)	J1
Strength dry (SD)	(SD3)
Strength green (SG)	(S1)
Bushfire resisting	Yes
Lyctine susceptibility	(SL)
Termite resistance	R
Advisory codes	

Target design life, hazard zones and conditions for use

Botanical name	<i>Eucalyptus sideroxylon</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	Approved
15 years In-ground:A	Approved
15 years In-ground:B	Approved

Botanical name	<i>Eucalyptus sideroxylon</i>
15 years In-ground:C	Approved
15 years In-ground:D	C1

Botanical name	<i>Eucalyptus sideroxylon</i>
50 years protected	Approved
50 years Above-ground:A	Approved
50 years Above-ground:B	Approved
50 years Above-ground:C	Approved
50 years Above-ground:D	Approved
50 years In-ground:A	C1
50 years In-ground:B	C7, C14
50 years In-ground:C	C8
50 years In-ground:D	C8

QTimber (<http://qtimber.daf.qld.gov.au>)
