



Properties

[Download pdf](#)

| | |
|--------------------------------|------------------------------------|
| Botanical name | <i>Eucalyptus marginata</i> |
| Synonyms | NA |
| Origin | Australia |
| Schedule | Schedule B |
| Hardwood | Yes |
| Density (kg/m3) | 835 |
| Durability above-ground | (2) |
| Durability in-ground | (2) |
| Hardness | H |
| Joint dry (JD) | JD2 |
| Joint green (JG) | J2 |
| Strength dry (SD) | (SD4) |
| Strength green (SG) | (S3) |
| Bushfire resisting | No |
| Lyctine susceptibility | (SL) |
| Termite resistance | R |
| Advisory codes | |

Target design life, hazard zones and conditions for use

| | |
|--------------------------------|------------------------------------|
| Botanical name | <i>Eucalyptus marginata</i> |
| 5 years above-ground | Approved |
| 15 years protected | Approved |
| 15 years Above-ground:A | Approved |
| 15 years Above-ground:B | Approved |
| 15 years Above-ground:C | Approved |
| 15 years Above-ground:D | Approved |
| 15 years In-ground:A | Approved |
| 15 years In-ground:B | C2 |
| 15 years In-ground:C | C3 |

| | |
|-----------------------------|------------------------------------|
| Botanical name | <i>Eucalyptus marginata</i> |
| 15 years In-ground:D | C4 |

| | |
|--------------------------------|------------------------------------|
| Botanical name | <i>Eucalyptus marginata</i> |
| 50 years protected | Approved |
| 50 years Above-ground:A | Approved |
| 50 years Above-ground:B | Approved |
| 50 years Above-ground:C | H3! |
| 50 years Above-ground:D | H3! |
| 50 years In-ground:A | C1, C11 |
| 50 years In-ground:B | C7, C11 |
| 50 years In-ground:C | C8, C11 |
| 50 years In-ground:D | C8, C11 |

QTimber (<http://qtimber.daf.qld.gov.au>)
