



Published on QTimber (<https://qtimber.daf.qld.gov.au>)

[Home](#) > [Timber Factsheet](#) >

Properties

[Download pdf](#)

Botanical name	<i>Pinus caribaea var. hondurensis</i>
Synonyms	NA
Origin	Asia-Pacific
Schedule	Schedule C
Hardwood	No
Density (kg/m³)	530-620
Durability above-ground	(4)
Durability in-ground	(4)
Hardness	S, F
Joint dry (JD)	JD4
Joint green (JG)	
Strength dry (SD)	(SD6)
Strength green (SG)	(S5)
Bushfire resisting	No
Lyctine susceptibility	NS
Termite resistance	R
Advisory codes	A5

Target design life, hazard zones and conditions for use

Botanical name	<i>Pinus caribaea var. hondurensis</i>
5 years above-ground	Approved
15 years protected	Approved
15 years Above-ground:A	Approved
15 years Above-ground:B	Approved
15 years Above-ground:C	Approved
15 years Above-ground:D	H3!
15 years In-ground:A	H4!
15 years In-ground:B	H4!
15 years In-ground:C	H4!

Botanical name	<i>Pinus caribaea var. hondurensis</i>
15 years In-ground:D	H4!

Botanical name	<i>Pinus caribaea var. hondurensis</i>
50 years protected	Approved
50 years Above-ground:A	H3!, C16
50 years Above-ground:B	H3!, C16
50 years Above-ground:C	H3!, C16
50 years Above-ground:D	H3!, C16
50 years In-ground:A	H5!
50 years In-ground:B	H5!
50 years In-ground:C	H5!
50 years In-ground:D	H5!

QTimber (<http://qtimber.daf.qld.gov.au>)
